



MEGAMIX SHOT A100



Applications

In the implementation of sprayed concrete, to reduce the return and fall of materials, it is necessary to use MEGAMIX SHOT A100 quick setting admixtures. This admixture can be used to apply dry or wet sprayed concrete for the stability of inclined surfaces, the inner surface of the excavated tunnel, the final layer of the tunnel cover, repair, etc.

One of the advantages of SHOT A100 is that it does not contain chloride for reinforced concrete. The fastness of this product makes it possible to use it to prevent water leakage, apply concrete on vertical surfaces and roofs, and achieve proper resistance in a short time.

Dosage

The consumption amount of RET 22 is recommended in the amount of 0.15 to 0.5% of the weight of cement materials. The amount of consumption is obtained according to the conditions of implementation, mixture design and laboratory tests.

Method of Use

SHOT A100 can be added to concrete or mortar in the spray concrete implementation in a more efficient way, at the head of the spray nozzle. After a short period of time, it starts to react.

This product can also be used in the application of dry sprayed concrete by adding this additive to the water used.

How to maintain

Store in a covered place, temperature more than 5°C, and inside the package.

Under the correct storage conditions and in the original packaging, it can be consumed up to 24 months after production.

Packaging:

25 kg gallon / 250 kg barrel / 1200 kg tank

Technical support

We are ready to provide related technical services in the site.

Compatibility

If you need to use it simultaneously with other additives, be sure to contact the technical support department.

Standard

This product complies with the INSO 2930-5 standard (table 2) as well as the EN 934-5 standard (table 2).

Technical features

Product Type: Liquid

Color: colorless to pale yellow

Specific mass (kg/L): 1.4 ± 0.02

pH: 13 ± 1

Amount of chloride: negligible (less than 0.1 percent)